

CLASS TEST

S.No. : 03 LS1_EC_C_310519

Electrtronic Devices & Circuits



MADE EASY

India's Best Institute for IES, GATE & PSUs

Delhi | Noida | Bhopal | Hyderabad | Jaipur | Lucknow | Indore | Pune | Bhubaneswar | Kolkata | Patna

Web: www.madeeasy.in | E-mail: info@madeeasy.in | Ph: 011-45124612

CLASS TEST 2019-2020

ELECTRONICS ENGINEERING

Electrtronic Devices & Circuits

Date of Test : 31/05/2019

Answer Key

- | | | | | |
|--------|---------|---------|---------|---------|
| 1. (c) | 7. (b) | 13. (c) | 19. (a) | 25. (c) |
| 2. (d) | 8. (c) | 14. (c) | 20. (b) | 26. (c) |
| 3. (a) | 9. (b) | 15. (a) | 21. (c) | 27. (b) |
| 4. (c) | 10. (b) | 16. (d) | 22. (d) | 28. (a) |
| 5. (b) | 11. (d) | 17. (d) | 23. (c) | 29. (b) |
| 6. (d) | 12. (b) | 18. (a) | 24. (d) | 30. (a) |

DETAILED EXPLANATIONS

2. (d)

Hall effect is used to determine the following

- * type of semiconductor
- * carries concentration
- * conductivity
- * mobility

5. (b)

$$\Delta T = 45 - 25 = 20^\circ\text{C}$$

$$\frac{dV}{dT} = -2.5 \text{ mV}/^\circ\text{C}$$

$$\Delta V = 2.5 \times 20 = 50 \text{ mV}$$

$$\therefore V_D = V - \Delta V = 625 \text{ mV} - 50 \text{ mV} = 575 \text{ mV.}$$

6. (d)

$$f_F(E_c) = \frac{1}{1 + \exp\left(\frac{E_c - E_f}{kT}\right)}$$

$$\approx \exp\left(\frac{-(E_c - E_f)}{kT}\right) = 9.69 \times 10^{-7}$$

7. (b)

According to mass-action law

$$np = n_i^2$$

$$n = \frac{n_i^2}{p} = \frac{(1.5 \times 10^{10})^2}{2.25 \times 10^{15}} = 1 \times 10^5 / \text{cm}^3$$

9. (b)

$$I_{CBO} = 500 \times 10^{-9} \left[2^{\frac{90-25}{10}} \right] = 45.25 \mu\text{A}$$

11. (d)

$$\text{Photocurrent} = 0.65 \times 10 \times 10^{-6} = 6.5 \mu\text{A}$$

12. (b)

$$g' = \frac{\Delta\rho}{\tau_p}$$

$$10^{26} = \frac{\Delta\rho}{2 \times 10^{-6}}$$

$$\Delta\rho = 2 \times 10^{20} \text{ m}^{-3}$$

$$= 2 \times 10^{14} \text{ cm}^{-3}$$

13. (c)

$$\frac{N_A}{N_D} = \frac{x_n}{x_p}$$

$$x_n = \left(\frac{N_A}{N_D} \right) (x_p)$$

$$x_n = \frac{1}{10} \times 0.5$$

$$x_n = 0.05 \mu\text{m}$$

$$x = x_n + x_p = 0.5 + 0.05 = 0.55 \mu\text{m}$$

14. (c)

$$J_p = -qD_p \frac{dp}{dx} = -1.6 \times 10^{-19} \times 20 \times 10^{12} \left(-\frac{1}{10^{-3}} \right) = 3.2 \text{ mA/cm}^2$$

$$I_p = J_p \times A = 3.2 \times 10^{-3} \times 1.25 \times 10^{-4} = 0.4 \mu\text{A}$$

15. (a)

$$\lambda \leq \frac{1.24}{E_g(\text{eV})} \mu\text{m}$$

For silicon

At

$$T = 300^\circ\text{K}$$

$$E_g = 1.1 \text{ eV}$$

so, wavelength λ at

$$E_g = 1.1 \text{ eV}$$

 \Rightarrow

$$\lambda \leq \frac{1.24}{1.1} \mu\text{m} = 1.13 \mu\text{m}$$

So clearly option (a) is out of the range.

16. (d)

As doping increases, Fermi level moves closer to the conduction band.

17. (d)

The percentage increase in the reverse saturation current is

$$\frac{I_{02}}{I_{01}} = 2^{(T_2 - T_1)/10} = 2^{(55 - 25)/10} = 8$$

$$\frac{I_{02} - I_{01}}{I_{01}} \times 100 = (8 - 1) \times 100 = 700\%$$

18. (a)

Zener breakdown voltage is less because it occurs in higher doping region.

Hence, zener breakdown voltage V_1 corresponds to point A.

19. (a)

$$E_i - E_F = kT \ln \frac{N_A}{N_i} = 26 \times 10^{-3} \ln \left(\frac{5 \times 10^{17}}{1.5 \times 10^{16}} \right) = 0.45 \text{ eV}$$

Since boron is p -type impurity, therefore fermi level goes down.

20. (b)

For n -type substrate, inversion occurs for higher negative voltage. So, point 1 corresponds to inversion. For low negative voltages, first the substrate becomes depleted of charge carriers and then inversion starts. The point at which inversion starts is threshold point i.e. point 2.

Point 3 corresponds to depletion region.

For positive voltage accumulation of electrons occurs in n -type substrate. Hence point 4 corresponds to accumulation.

21. (c)

$$I_0 = qA \left(\frac{D_p}{L_p} p_{r0} + \frac{D_n}{L_n} n_{p0} \right)$$

As
 $\Rightarrow n_{p0}$ is negligible

$$N_A \gg N_D$$

$$I_0 \approx \frac{qAD_p}{L_p} p_{r0}$$

$$p_{r0} = \frac{n_i^2}{N_D}$$

$$I_0 = \frac{1.6 \times 10^{-19} \times 10^{-3} \times 10 \times 4.5 \times 10^3}{3.16 \times 10^{-3}} \times \frac{2.25 \times 10^{20}}{5 \times 10^{16}}$$

$$I_0 = 2.278 \times 10^{-15} \text{ A}$$

$$|I_r| \approx |I_0|$$

$$[I_r = I_0(e^{-V/nV_T} - 1)]$$

$$|I_r| = 2.278 \times 10^{-15} \text{ A}$$

22. (d)

n = new concentration of electrons at the surface

n_0 = equilibrium concentration of electrons

$$n_0 = \frac{n_i^2}{p_0} \approx \frac{n_i^2}{N_A} = 1.8 \times 10^5 \text{ cm}^{-3}$$

$$n = n_0 e^{\Psi/V_t}; \quad V_t = \frac{kT}{q}, \quad \Psi = \text{surface potential}$$

$$\Psi = \frac{kT}{q} \ln\left(\frac{n}{n_0}\right) = 0.026 \ln\left(\frac{3 \times 10^{10}}{1.8}\right) \approx 0.612 \text{ V}$$

23. (c)

$$I_{D,\text{sat}} = \frac{W\mu_n C_{ox}}{2L} (V_{GS} - V_T)^2$$

$$4 \times 10^{-3} = \frac{W(650)(6.9 \times 10^{-8})}{2(1.25 \times 10^{-4})} (5 - 0.65)^2$$

$$W = 11.8 \mu\text{m}$$

24. (d)

$$I_C = \beta I_B + (1 + \beta)I_{CO}$$

$$\beta = \frac{\alpha}{1 - \alpha} = \frac{0.98}{1 - 0.98} = 49$$

$$\therefore I_C = 49 \times 20 + 50 \times 0.6 = 980 + 30 = 1010 \mu\text{A}$$

$$\text{or } I_C = 1.01 \text{ mA}$$

25. (c)

In linear region

$$I_D = \mu_n C_{ox} \frac{W}{L} \left((V_{GS} - V_T) V_{DS} - \frac{V_{DS}^2}{2} \right)$$

$$\left(\frac{\partial I_D}{\partial V_{GS}} \right)_{\text{linear}} = k'_n V_{DS} \quad \dots(1)$$

In saturation region

$$I_D = k(V_{GS} - V_T)^2$$

$$\left(\frac{\partial I_D}{\partial V_{GS}} \right)_{\text{saturation}} = 2k(V_{GS} - V_T) \quad \dots(2)$$

$$\frac{\left(\frac{\partial I_D}{\partial V_{GS}} \right)_{\text{linear}}}{\left(\frac{\partial I_D}{\partial V_{GS}} \right)_{\text{saturation}}} = \frac{k'_n V_{DS}}{2k(V_{GS} - V_T)}$$

$$\frac{\left(\frac{\partial I_D}{\partial V_{GS}} \right)_{\text{linear}}}{\left(\frac{\partial I_D}{\partial V_{GS}} \right)_{\text{saturation}}} = \frac{2k V_{DS}}{2k(V_{GS} - V_T)} = \frac{V_{DS}}{(V_{GS} - V_T)}$$

$$\left[\begin{array}{l} \text{(here } k_n = \mu_n C_{ox} \text{)} \\ k'_n = k_n \left(\frac{W}{L} \right) \\ k = \frac{1}{2} \mu_n C_{ox} \frac{W}{L} \\ k = \frac{1}{2} k'_n \\ k'_n = 2k \end{array} \right]$$

26. (c)

$$C \propto \frac{1}{\sqrt{V_{bi} + V_{RB}}}$$

$$\frac{C_1}{C_2} = \frac{\sqrt{V_{bi} + V_{RB2}}}{\sqrt{V_{bi} + V_{RB1}}}$$

$$\text{at } V_{RB1} = 0 \text{ V, } C_1 = 1 \mu\text{F.}$$

$$\text{at } V_{RB2} = 6 \text{ V, } C_2 = 0.5 \mu\text{F.}$$

$$\frac{1}{0.5} = \frac{\sqrt{V_{bi} + 6}}{\sqrt{V_{bi} + 0}}$$

$$2 = \frac{\sqrt{V_{bi} + 6}}{\sqrt{V_{bi}}}$$

$$4 V_{bi} = V_{bi} + 6$$

$$3V_{bi} = 6$$

$$V_{bi} = 2 \text{ V}$$

27. (b)

Given the probability of state being empty is 0.9258

i.e. $1 - f(E) = 0.9258$

The energy level being occupied by electron is $f(E)$

$\therefore f(E) = 1 - 0.9258 = 0.0742$

$$f(E) = \frac{1}{1 + e^{\left(\frac{E - E_F}{kT}\right)}}$$

$$0.0742 = \frac{1}{1 + e^{\left(\frac{E - E_F}{kT}\right)}}$$

$$1 + e^{\left(\frac{E - E_F}{kT}\right)} = 13.477$$

$$\frac{E - E_F}{kT} = 2.523$$

$\therefore E - E_F \approx 2.52 \text{ kT}$

$$E = E_F + 2.52 \text{ kT}$$

The energy level 2.52 kT above the Fermi energy is occupied by electron with probability 0.0742.

28. (a)

We know that electrical neutrality condition

$$N_D + P = N_A + n$$

for lightly doped P -type semiconductor

$$N_D = 0$$

$\therefore P = N_A + n$

$$N_A = P - n$$

$$= P - \frac{n_i^2}{P} = n_i \sqrt{\frac{\mu_n}{\mu_p}} - \frac{n_i^2}{n_i \sqrt{\mu_p}}$$

$$N_A = n_i \left[\left(\frac{\mu_n}{\mu_p} \right)^{\frac{1}{2}} - \left(\frac{\mu_p}{\mu_n} \right)^{\frac{1}{2}} \right] = 2.4 \times 10^{10} \left[\sqrt{9} - \sqrt{\frac{1}{9}} \right]$$

$$N_A = 6.4 \times 10^{10} \text{ cm}^{-3}$$

29. (b)

Phosphorous is a pentavalent atom when it is added as a dopant with Si sample it behaves as a n-type semiconductor and Boron is a trivalent atom when it is added as a impurities with Si sample it behaves as a p-type semiconductor. When both the atoms as a donar and acceptor atoms are added together then it will neutralised to each-other, and as per the given concentration the net charge will be 10^{16} Boron atoms, so it will behave as p-type, semiconductor with net carrier concentration of $10^{16}/\text{cm}^3$.

30. (a)

$$I_D = 0.4 \text{ mA}, V_D = 0.5 \text{ V}$$

$$R_D = \frac{V_{DD} - V_D}{I_D} \Rightarrow R_D = 5 \text{ k}\Omega$$

Since $V_D = 0.5 \text{ V}$ is greater than V_G , this means the NMOS transistor is operating in the saturation region.

$$I_D = \frac{1}{2} \mu_n C_{ox} \frac{W}{L} (V_{GS} - V_t)^2$$

$$\Rightarrow$$

$$V_{GS} - V_t = 0.5 \text{ V}$$

$$\Rightarrow$$

$$V_{GS} = V_t + 0.5 = 1.2 \text{ V}$$

$$R_S = \frac{V_S - V_{SS}}{I_D} = \frac{-V_{GS} - V_{SS}}{I_D} = \frac{1.3}{0.4} \text{ k}\Omega = 3.25 \text{ k}\Omega$$

■■■■